

Fillite SG(500) - RN

Omya UK Limited Melton Office Melton Bottom Melton North Ferriby East Riding of Yorkshire **HU14 3HU**

Tel +44 (0) 1482 636800

Fax +44 (0) 1482 636880

SITE:

RUNCORN, Great Britain

SHORT DESCRIPTION OF THE PRODUCT:

Fillite is a lightweight, free flowing, spherical, glass hard, inert, hollow silicate sphere. It is primarily used to reduce the weight of materials but also imparts further benefits in many applications such as filler loading and improved rheological properties as a direct attribute to their spherical shape.

CHEMICAL PROPERTIES OF SHELL & GAS:

SiO ₂	55.0 - 65.0	%
Al_2O_3	27.0 - 33.0	%
Fe ₂ O ₃	≤6	%
CO ₂ content in the spheres	70	%
N ₂ content in the spheres	30	%
Loss on ignition (1000°C)	≤2	%

SPECIFIC PRODUCT DATA:

Fineness:

· Passing 500 µm sieve (ISO 787/7)	99.5 - 100.00	0/2
9 1 , ,		
· Passing 300 µm sieve (ISO 787/7)	85.0 – 100.0	%
· Passing 150 µm sieve (ISO 787/7)	30.0 - 80.0	%
· Passing 106 µm sieve (ISO 787/7)	25.0 - 55.0	%
· Passing 50 µm sieve (ISO 787/7)	2.0 - 10.0	%
Moisture ex works (ISO 787/2)	≤0.3	%
Colour Croy		

Colour - Grev

GENERAL PRODUCT DATA:

Loose bulk density (ISO 787/11)	0.35 - 0.48	g/cc (27 lbs/ft ³)
Packing factor	60.0 - 65.0	%
Mohs Scale hardness of shell	5	
Average wall thickness of sphere diameter	5.0 - 10.0	%
Melting temperature	1200 - 1350	
Thermal conductivity		Wm ⁻¹ K ⁻¹
Typical crush strength	(105 – 210	kg/cm ²
	(1500 - 3000	psi

The above tables contain average results for this product.

MAIN APPLICATIONS:

Refractories Resins **Low Density Cements Sound Dampening Sheets Mortars & Grouts**

The information contained in the Technical Data Sheet relates only to the specific material designated herein and does not relate to use in combination with any other material or in any process. The information provided herein is based on technical data that Omya believes to be reliable, however Omya makes no representation or warranty as to the completeness of accuracy thereof and Omya assumes no liability resulting from its use or for claims, losses, or damages of any third party. Recipients receiving this information must exercise their own judgement as to the appropriateness of its use, and it is the user's responsibility to assess the materials suitability (including safety) for a particular purpose prior to such use.

edition: 27.02.2014 S08.03.01_EN_CORP\GBRN_I1005565_00 version: 6

[®] Registered Trademark of the Omya Group